

Technical Data Sheet



W V C O

Willamette Valley Company

www.wilvaco.com

800.333.9826

Partnering through
service, innovation, and
integrity

WESTERN DIVISION

660 McKinley Street
Eugene OR 97402
Tel. 800.333.9826

EASTERN DIVISION

6662 Marbut Road
Lithonia GA 30058
Tel. 888.878.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors MN 55616
Tel. 218 834 3922

SOUTHERN DIVISION

100 Dixie Mae Drive
Pineville LA 71361
Tel. 800 444 9826

CBS-197H Sealer Clear HV

Edge/End Sealer for Dimensional Lumber and Composite Boards

DESCRIPTION

Willamette Valley Company has formulated CBS-197H Sealer Clear HV, as a high quality, 45% solids, sealer specifically designed to protect against moisture. CBS-197H maintains the dimensional stability of the lumber and panels exposed to moisture by forming an elastomeric film barrier that fills voids, and is both effective and long lasting. Additionally, CBS-197H exhibits high performance on plywood, overlaid panels, particle board and other applications.

WHERE TO USE

- Dimensional Lumber End Seal
- Composite Board Edge Sealer
- Engineered Lumber
- Industrial Mill Environments

FEATURES AND BENEFITS

- Excellent Moisture Protection
- Increases Wood Shelf Life
- Fills Voids to Seal Effectively
- Long Lasting Moisture Barrier
-

PACKAGING

5 gallon pails
Drums
Totes
Tanker

SHELF LIFE

3 months when properly stored. **Will require agitation.**

STORAGE

Store this product in a clean, dry, shaded or covered environment above 45°F (7.2°C). DO NOT FREEZE.

TECHNICAL INFORMATION

TYPICAL PROPERTIES

Weight / Gallon – lbs./gallon, (Kg / L) (varies dependent on color)	8.0 (0.96)
Coverage, sq. ft. / U.S. gallon (m sq./ L)	300 (7.4)
Solids by weight	45%
Viscosity at 78°F (25.5°C) (centipoise)	2500-3500
Clear	

APPLICATION

CBS-197H Sealer Clear HV can be applied in several ways. Apply one coat of CBS-197H Sealer Clear HV by HVLP or airless spray at a film thickness of 8-10 wet mils. It can also be applied by brush or roller. You can increase the film thickness for porous wood or to obtain a higher performance. Check with your Willamette Valley Company representative for directions and recommendations for use with other types of application methods. Stenciling or any recoating process should be done before the sealer has dried completely and formed an impervious film.

CLEAN-UP

The CBS-197H Sealer Clear HV can be washed off with water prior to the film drying. If the sealer has dried, scrubbing with hot water and detergent is advised.

NOTES

This product is supplied to the customer in a ready to use form. Any addition of water will result in degradation of the product performance.

HEALTH AND SAFETY

Before handling, you should become familiar with the Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an SDS please call 800-333-9826 or send an email to: msds@wilvaco.com.

CONTACT INFORMATION

Please see the side bar on the right and the front page for the Division nearest to your location.

WILLAMETTE VALLEY COMPANY

www.wilvaco.com

info@wilvaco.com

OTHER DIVISIONS

PERFORMANCE COATINGS

1075 Arrowsmith Street

PO Box 2280

Eugene, OR 97402

Tel 541.484.9621

www.POLYQUIK.com

www.wvcorailroad.com

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street

Eugene, OR 97402

Tel 541.484.2368

www.pre-tec.com

CANADIAN DIVISION SURREY BRANCH

19081- 27th Avenue

Surrey BC V3S 5T1

Tel. 800.663.4298

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office

1075 Arrowsmith Street

Eugene, OR 97402

Tel 541.284.4667

www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy

PO Box 188

Malad City, Idaho 83252

Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625

Parque Industrial Coronel

Coronel, Chile

Tel 011.56.412.928.100

www.tapel.cl



W07-R&D-TDS-026

REV01

Revision Date: April 2016

DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE.