

Technical  
Data Sheet



Willamette Valley Company

www.wilvaco.com

800.333.9826

Partnering through service,  
innovation, and integrity

# POLYQuik<sup>®</sup> Aluminum Primer (SB)

## Fast Drying Primer for Aluminum Surfaces

### DESCRIPTION

POLYQuik<sup>®</sup> Aluminum Primer (SB) is an ULTRA-LOW VOC primer that dries quickly to provide excellent spray elastomer adhesion to aluminum surfaces. Aluminum Primer (SB) is easy to apply with a HVLP spray gun to a degreased, non-abraded aluminum surface, just prior to applying a spray elastomer topcoat.

### WHERE TO USE

- **Walls & Floors**—clean aluminum surface
- **Under Coatings**—spray elastomer coatings
- **Aluminum Substrates**—parts or flat surfaces
- **OEM Operations**—fast production requirements

### FEATURES AND BENEFITS

- **Superior Adhesion**—clean aluminum surfaces
- **Ultra-Low VOC**—0.09 lbs/gal VOC
- **Non-hazardous Pigments**—free of chromates
- **Fast Drying**—dries quickly in humid conditions

### PACKAGING

1 gallon (3.78 L) Kit

### COLORS

Black

### YIELD

1300 sq.ft. per gallon at 1.0 mils  
(120 sq. m. per liter at 0.025 mm)

### SHELF LIFE

1 year(s) when properly stored.

### STORAGE

Store and ship this product in a clean, dry, low-humidity, shaded or covered environment at 60 to 90° F (15 to 32° C).

## TECHNICAL INFORMATION

### Typical Properties

<b>VOC</b> , lbs/gal (g/L), ASTM D 2369	0.09
<b>Viscosity</b> , cps, ASTM D 4878, mixed	20
<b>Service temperature</b> , ° F (° C)	-22 to 135 (-30 to 57)
<b>Potlife</b> , minutes	60
<b>Ready for topcoat</b> , minutes	15 to 120 at 70°F (20°C)
<b>Topcoat Adhesion</b> , max. lbf/in (N/m), ASTM D 903	28 (topcoat cohesive failure)

### Cure Time

Temperature, 50% RH	Ready for topcoat, minutes	Maximum recoat time, hrs
50° F (10° C)	30	3
70° F (21° C)	15	2
104° F (40° C)	10	1

### Processing Parameters

<b>Ratio by volume</b> , (Part A to Part B)	1 to 10
<b>Application temp</b> , ° F (° C)	50 to 105 (10 to 40)
<b>Recommended thick.</b> , mils (mm)	0.5 to 1.0 (0.012 to 0.02)
<b>Spray equipment</b> , tip (mm), psi (bar)	HVLP Siphon or HVLP Gravity 0.071-0.087" (1.8-2.2), 10 (0.8)

---

## APPLICATION

---

### SURFACE PREPARATION

1. Remove any sharp edges and other surface imperfections.
2. Degrease surfaces with metal cleaner and a lint-free cloth.
3. For maximum adhesion, abrade surface with a red scuffing pad or a #80 sand paper. Degrease abraded surfaces with metal cleaner.
4. Apply coating only if steel surface temperature is 5° F (3° C) above the dew point to avoid application over damp surface.
5. Apply primer and topcoat within the 2 hours and before the prepared surface is chemically contaminated. Re-clean surface that has been contaminated before applying primer or topcoat.
6. Mask off any area that is not to be primed.

### PROCESSING

1. Precondition the containers to 70°F (21°C) for 24 hours before using. Choose a work area that is shaded and away from direct sunlight.
2. Part B must be mixed in its original container before Part A and Part B are combined. Slowly mix Part B with a mixing stick until all pigment is distributed and color is uniform (usually 3 to 5 minutes).
3. Use marked containers to measure exact ratio of Part A and Part B. Choose a final volume that can be easily applied within 30 minutes.
4. Mixing containers must be clean and dry. Do not use containers contaminated with water or other liquids.

### APPLICATION

1. Apply POLYQuik® Aluminum Primer (SB) no more than 1 wet mil (0.025mm). Applications thicker than 1 wet mil will result in poor primer performance and possible adhesive failure of the topcoat.
2. Before priming, protect adjacent surfaces with tape or other kinds of protective barriers.

3. Begin priming only if the topcoat can be applied within 2 hours of primer application. Make sure primer does not puddle, run, or build up in crevices.
4. Proper application is the responsibility of the user. Field visits by WVCO Representative are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

### SPRAY APPLICATION

1. This method is recommended for priming large areas, vertical areas, and narrow spaces.
2. Wear proper respiratory protection and other protective gear while spraying.
3. Use a HVLP spray gun fitted with a 0.071-0.087" (1.8-2.2 mm) tip and set at an air pressure of 10 psi (0.8 bar).

NOTE: Potlife of mixed material is 60 minutes. Topcoats must be applied before primer becomes contaminated. If topcoat time is exceeded, mechanically remove primer, degrease, and re-prime area.

### CLEANING & MAINTENANCE

- Clean equipment with POLYQuik® Cleaner or acetone immediately after use. Cured material must be removed mechanically.

---

## HEALTH AND SAFETY

---

Willamette Valley Company recommends reading and becoming familiar with the MSDS before using this product.

### WILLAMETTE VALLEY COMPANY

[www.wilvaco.com](http://www.wilvaco.com)  
[info@wilvaco.com](mailto:info@wilvaco.com)

### DIVISIONS

#### WESTERN DIVISION

1075 Arrowsmith Street  
PO Box 2280  
Eugene, OR 97402  
Tel 541.484.9621  
[www.POLYQUIK.com](http://www.POLYQUIK.com)  
[www.SPIKEFAST.com](http://www.SPIKEFAST.com)

#### EASTERN DIVISION

6662 Marbut Road  
Lithonia, GA 30058  
Tel 888.878.9826

#### MIDWEST DIVISION

1549 Hwy 2  
Two Harbors, MN 55616  
Tel 218.834.3922

#### PRECISION TECHNOLOGIES DIVISION

675 McKinley Street  
Eugene, OR 97402  
Tel 541.484.2368  
[www.pre-tec.com](http://www.pre-tec.com)

#### SOUTHERN DIVISION

100 Dixie Mae Drive  
PO Box 4450  
Pineville, Louisiana 71361  
Tel 318.640.5077

### SUBSIDIARIES

#### CANADIAN WILLAMETTE

325 Edworthy Way  
New Westminster BC V3L 5G4  
Tel. 800.663.4298

#### ECLECTIC PRODUCTS INC.

Corporate Office  
1075 Arrowsmith Street  
Eugene, OR 97402  
Tel 541.284.4667  
[www.eclecticproducts.com](http://www.eclecticproducts.com)

#### IDAHO MILL & GRAIN

445 North 430 West Hwy  
Po Box 188  
Malad City, Idaho 83252  
Tel 208.766.2206

#### TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625 Parque  
Industrial Coronel Coronel, Chile  
Tel 011.56.41.928.100  
[www.tapel.cl](http://www.tapel.cl)



---

### DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE.

Revision Date 3-2008