



Willamette Valley Company

www.wilvaco.com

www.polyquik.com

800.333.9826

Partnering through service,
innovation, and integrity

FastPatch 5000

High Strength Concrete Repair

DESCRIPTION

FastPatch 5000 is a flexible and tough concrete repair material with excellent adhesion. FastPatch 5000 is a 100% solids, 2-component urethane designed to meet 5,000 psi compression strength requirements combined with excellent flexibility and resilience. Areas repaired with FastPatch 5000 can be re-opened to traffic in less than one hour.

WHERE TO USE

- Roads/Highways
- Bridges
- Warehouse Floors
- Parking Decks
- Sidewalks
- Any Crack or Spall in Concrete Needing Repair

FEATURES AND BENEFITS

- Rapid Cure— as little as 1 hour return to service
- 100% Solids, no odor
- 1:1 Ratio by Volume—easy application
- Excellent Concrete Adhesion
- Minimal Equipment Requirements
- Ideal for concrete repairs where high strength material is required

PACKAGING

20-oz. (600 mL) Cartridge
50-oz. (1500 mL) Cartridge

FastPatch 5000 Kit (aggregate included)
FastPatch 5000 High-Yield Kit

5-Gallon (19-Liter) Pail
50-Gallon (190-Liter) Drum
200-Gallon (757-Liter) Tote

COLORS

Gray

SHELF LIFE

1 year when properly stored.

STORAGE

Store and ship this product in clean, dry, low-humidity, and shaded or covered environments between 50 and 90°F (10-32°C)

TYPICAL PROPERTIES

	Result	ASTM
Solids Content	100%, SCAQMD compliant	D2369
Tack-Free Time	10 minutes	C679
Concrete Adhesion, Unprimed	600 psi (4.1 MPa), concrete failure	D4541
Concrete Adhesion, Primed	1,200 psi (8.3 MPa), concrete failure	D4541
Compression Strength, gravel aggregate, 3.5 hour ambient cure	1,500 psi (10.3 MPa)	C109
Compression Strength, gravel aggregate, 158°F (70°C) overnight cure	5,000 psi (34.5 MPa)	C109
Hardness	70 Shore D	C661
Mix Ratio (by Volume)	1:1	-

APPLICATION INSTRUCTIONS

For instructions on how to handle and apply FastPatch 5000 from cartridges, please refer to [POLYQuik® Cartridge Instructions](#). For handling and applying from kits: [POLYQuik® Kit Instructions](#). For applications with WVCO/Pre-Tec metering equipment, training will be provided. If you have specific questions related to your dispensing equipment, please contact your WVCO representative or customer support.

For concrete spall and crack repair guidelines, please refer to:

[POLYQuik® Concrete Spall and Crack Repair Guidelines](#)

For bridge header repair guidelines, please refer to: [POLYQuik®](#)

[Bridge Header and Joint Installation Guidelines](#)

ESTIMATED COVERAGE

Crack filling (without aggregate)

Crack Dimensions	Linear Feet (Meter) per 20-oz. (600-mL) Cartridge	Linear Feet (Meter) per Gallon (3.8-Liter)
1/8' x 1/2' (3.2 x 12.7 mm)	14.8 (4.5)	95 (29)
1/4' x 1/2' (6.4 x 12.7 mm)	7.4 (2.3)	47 (14)
1/2' x 1/2' (12.7 x 12.7 mm)	3.7 (1.1)	24 (7.2)
1' x 1/2' (25.4 x 12.7 mm)	1.8 (0.6)	12 (3.6)

Concrete repair yield-volumes are with aggregate. Coverage area assumes 2" (51 mm) average repair depth.

	Yield	Coverage Area ft ² (m ²)
20-oz (600-mL) cart.	90 in ³ (1.5-liters)	0.31 (0.03)
50-oz (1500-mL) cart.	225 in ³ (3.7-liters)	0.78 (0.07)
1-gallon (3.8-liter) of mixed material	2.5-gallons (9.5-liters)	2.01 (0.19)
FastPatch 5000 Kit	2.5-gallons (9.5-liters)	2.01 (0.19)
FastPatch 5000 High Yield Kit	5-gallons (19-liters)	4.01 (0.373)

HEALTH AND SAFETY

Before handling, you should become familiar with the Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an SDS, please call 800-333-9826 or send an email to: msds@wilvaco.com.

DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE. PROPER APPLICATION IS THE RESPONSIBILITY OF THE USER. AS WITH ANY PRODUCT THE USE OF THIS PRODUCT IN A GIVEN APPLICATION MUST BE TESTED (INCLUDING BUT NOT LIMITED TO FIELD TESTING) IN ADVANCE BY THE USER TO DETERMINE SUITABILITY. TESTING IS THE REQUIREMENT OF BOTH ENGINEERS AND CONTRACTORS ALIKE. WVCO DOES NOT WARRANT THE APPLICATION UNDER ANY OR ALL CIRCUMSTANCES.

WILLAMETTE VALLEY COMPANY
www.wilvaco.com
info@wilvaco.com

DIVISIONS WESTERN

DIVISION

1075 Arrowsmith Street
PO Box 2280
Eugene, OR 97402
Tel 541.484.9621
www.POLYQUIK.com
www.SPIKEFAST.com

EASTERN DIVISION

6662 Marbut Road
Lithonia, GA 30058
Tel 888.878.9826

MIDWEST DIVISION

1549 Hwy 2
Two Harbors, MN 55616
Tel 218.834.3922

PRECISION TECHNOLOGIES DIVISION

675 McKinley Street
Eugene, OR 97402
Tel 541.484.2368
www.pre-tec.com

SOUTHERN DIVISION

100 Dixie Mae Drive
PO Box 4450
Pineville, Louisiana 71361
Tel 318.640.5077

SUBSIDIARIES

ECLECTIC PRODUCTS INC.

Corporate Office
1075 Arrowsmith Street
Eugene, OR 97402
Tel 541.284.4667
www.eclecticproducts.com

IDAHO MILL & GRAIN

445 North 430 West Hwy
PO Box 188
Malad City, Idaho 83252
Tel 208.766.2206

TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625
Parque Industrial Coronel
Coronel, Chile
Tel 011.56.41.2.928.100
www.tapel.cl



W07-R&D-TDS-023
REV 00
Revision Date: March 2016